

# SUPER EXTRA

**Sustainably** oriented, EverZinc's distilled zinc powder is produced from **recycled zinc**. Our products are extensively used in the manufacturing of **liquid and powder coatings** and complies with ASTM D520 Type I and Type II (EP).

- Applications :**
- . Zinc primers (silicates, epoxies, polyurethanes... both solventborne and waterborne)
  - . Shop primers
  - . Mechanical plating
  - . Sherardizing
  - . Cold galvanizing
  - . Zinc flakes
  - . Thermal spray

- Packaging :**
- (UN approved)
- . Paper bags **25kg**
  - . Metal drums **6-100kg**
  - . Big bags **250-1500kg**

- Shelf Life :**
- (Recommended)
- . Paper bags **12 months**
  - . Metal drums **12 months**
  - . Big bags **12 months**

- Storage :**
- Indoor in a dry ventilated location.
- To maximize the shelf life and maintain product integrity, do not open the packaging until the material is to be used.

Physical data	Standard/Method	Specification
Particle size (x50)	Sympatec	1,7 µm - 3,8 µm
Sieve residue at 45µm	ISO 3549/Brushing	≤ 0,01%
Oil Absorption	ASTM D281/Titration	6,50%

Chemical data	Standard/Method	Type I	Type II (EP)
Total zinc	Calculation	≥ 98,5%	≥ 98,5%
Metallic zinc	Gas evolution	≥ 94%	≥ 94%
Pb	ISO 3549/ICP-OES	≤ 0.1%	≤ 0.01%
Cd	ISO 3549/ICP-OES	≤ 0.04%	≤ 0.01%
Fe	ISO 3549/ICP-OES	≤ 0.005%	≤ 0.005%

The information contained herein has been compiled to the best of EverZinc' knowledge and is presented without any obligation.

**EverZinc Norway A/S**  
**Plant & Commercial Offices**

Hoffsgt,10  
3262 Larvik  
Norway  
Phone: +47 33 18 09 50  
Website: [www.everzinc.com](http://www.everzinc.com)

**EverZinc HQ**

Fullbright Tower, Mc Kinney 1301, Ste 1575  
Houston, TX 77010  
USA

